


TPX

Temperature Programmed Techniques

Dr. Davide Ferri
Paul Scherrer Institut
 056 310 27 81
 davide.ferri@psi.ch

Definitions

- Temperature programmed desorption (TPD), or thermal desorption spectroscopy (TDS)
- Temperature programmed reduction (TPR)
- Temperature programmed reaction (TPR)
- Temperature programmed oxidation (TPO)
- Temperature programmed reaction spectroscopy (TPRS)



Definitions

- **TPD**


A solid is first exposed to an adsorbate gas under well-defined conditions (temperature and pressure) and then heated under inert conditions with a temperature program

- **TPX but TPD**

Solid and reactants in contact during temperature programmed experiment

Information

- T_{red} , T_{des} , T_{ox} , T_{react}
 - Adsorption site strength, quality and quantity
 - Bond strength, solid-adsorbate
 - Surface coverage
 - Quantification of desorption
 - Adsorption enthalpy + pre-exponential factor for desorption
-
- **Advantages**
 - Experimentally simple
 - Inexpensive
 - Access to powders and single crystals
 - **Disadvantages**
 - Complex determination of activation energies and pre-exponential factors




Temperature programmed techniques

■ Equipment

Thermal conductivity

gas	$\lambda \times 10^{-3}$ [W/(cmK)]
air	0.277
NH ₃	0.270
Ar	0.190
CO ₂	0.183
CO	0.267
He	1.574
H ₂	1.972
CH ₄	0.374
N ₂	0.275
O ₂	0.285
H ₂ O	0.195




Reactant and carrier gases

TPR: 5 vol.% H₂/Ar (or He)

TPO: 5 vol.% O₂/He

Temperature programmed reduction

- Reduction of a bulk metal oxide



From thermodynamics:

$$\Delta G = \Delta G^0 + nRT \ln(p_{\text{H}_2\text{O}}/p_{\text{H}_2}) < 0$$

If H_2 is the reducing agent,


$$\Delta G = nRT \ln[(p_{\text{H}_2\text{O}}/p_{\text{H}_2})/(p_{\text{H}_2\text{O}}/p_{\text{H}_2})_{\text{eq}}]$$

then $\Delta G < 0$, if

$$p_{\text{H}_2\text{O}}/p_{\text{H}_2} < (p_{\text{H}_2\text{O}}/p_{\text{H}_2})_{\text{eq}}$$

Temperature programmed reduction

- Reduction of a bulk metal oxide



thermodynamic data for reduction (400°C)

metal	oxide	$(p_{\text{H}_2\text{O}}/p_{\text{H}_2})_{\text{eq}}$
Ti	TiO_2	4×10^{-16}
	TiO	2×10^{-9}
V	V_2O_5	6×10^{-4}
	VO	2×10^{-11}
Cr	Cr_2O_3	3×10^{-9}
	MnO_2	10
Mn	MnO	2×10^{-10}
	Fe	0.7
Fe	Fe_2O_3	0.1
	FeO	50
Co	NiO	500
	CuO	2×10^8
Ni	Cu_2O	2×10^6
	MoO ₃	40
Cu	MoO_2	0.02
	RuO ₂	10^{12}
Mo	RhO	10^{13}
	PdO	10^{14}
Ru	Ag ₂ O	3×10^{17}
	IrO ₂	10^{13}

BUT!

reduction of a supported MO_x can produce completely different TPR patterns

Temperature programmed reduction

■ Reduction mechanisms



$$- d[\text{MO}_n]/dt = k_{\text{red}} [\text{H}_2]^p f([\text{MO}_n])$$

k_{red} , rate constant of reduction reaction

p, reaction order in H_2

t, time

If α is the degree of reduction, if $p=0$ (excess H_2), if linear T-ramp ($dT = \beta dt$) and using Arrhenius equation

$$d\alpha/dT = v/\beta e^{-E_{\text{red}}/RT} f(1-\alpha)$$


v, pre-exponential factor

β , heating rate


E_{red} , activation energy of reduction reaction

Temperature programmed reduction

- Reduction mechanisms



shrinking core



$$f(\alpha) = 3 (1-\alpha)^{1/3}$$

nucleation and growth




$$f(\alpha) = (1-\alpha)[- \ln(1-\alpha)]^{2/3}$$

Temperature programmed reduction

- Activation energy of reduction

$$\ln(\beta/T_{\max}^2) = -E_{\text{red}}/RT_{\max} + \ln(vR/E_{\text{red}}) + K$$


if $f(1-\alpha)$ and $\alpha(T_{\max})$ independent of β .



Temperature programmed reduction

■ Reduction of a bulk metal oxide

...a somewhat different phase diagram





three-steps mechanism
two-steps mechanism

one-step mechanism?
 $\text{Fe}_2\text{O}_3 \rightarrow \text{Fe}$

Temperature programmed reduction



■ Effect of exp. conditions



- TPR profile dependent on exp. Conditions
 - sample amount, H_2 conc., H_2O , T ramp...
- Effect of fed water on $p_{\text{H}_2\text{O}}/p_{\text{H}_2}$?

Temperature programmed reduction


■ Evidence of mechanism from XRD



- Effect of fed water on $p_{\text{H}_2\text{O}}/p_{\text{H}_2}$
 - High ratio, three step mechanism
 - Low ratio, two step mechanism


Temperature programmed reduction

■ Evidence of mechanism from XRD



Temperature programmed reduction




- Supported oxides and bimetallic catalysts



Temperature programmed reduction



■ Reduction mechanisms, PrCoO_3

- $\text{Co}^{3+} + 1\text{e}^- \rightarrow \text{Co}^{2+}$
- $\text{Co}^{2+} + 2\text{e}^- \rightarrow \text{Co}$




Temperature programmed reduction

- Reduction of 0.5 wt.% Pd/LaCoO₃: H₂-TPR XRD





No information on Pd



Temperature programmed reduction


- Reduction of 0.5 wt.% Pd/LaCoO₃: H₂-TPR XANES





Temperature programmed reduction

■ Reduction of Pd-containing perovskites

2 wt.% Pd/LaFeO₃



LaFe_{0.95}Pd_{0.05}O₃




10 vol.% H₂/He, 10°C/min, 50 ml/min

Eyssler et al., J. Phys. Chem. C 114 (2010) 4584

Temperature programmed reduction

■ Reduction of Pd-containing perovskites




10 vol.% H₂/He, 10°C/min, 50 ml/min


Eyssler et al., J. Phys. Chem. C 114 (2010) 4584

Temperature programmed reduction

■ Reduction of CeO_2 -based catalysts





Red. conditions: $\text{CeO}_2 \rightarrow \text{Ce}_2\text{O}_3$
Ox. conditions: $\text{Ce}_2\text{O}_3 \rightarrow \text{CeO}_2$



Temperature programmed desorption

- Oxygen mobility in perovskite-type oxides – O₂-TPD
 - surface oxygen (α): suprafacial catalysis
 - lattice oxygen (β): intrafacial catalysis



$$t = \frac{r_A + r_O}{\sqrt{2}(r_B + r_O)}$$

Temperature programmed desorption

■ Distribution of acid sites – NH₃-TPD

- which sites are present?
- how strong are the sites?
- which sites are catalytic relevant?
- site structure?



- NH₃ ads. at given T
- NH₃ desorption upon heating

