Deterministic and stochastic aspects of current-induced magnetization reversal in perpendicular nanomagnets

G. Sala[®],^{*} J. Meyer, A. Flechsig, L. Gabriel[®], and P. Gambardella[†] Department of Materials, ETH Zurich, 8093 Zurich, Switzerland

(Received 13 January 2023; revised 4 June 2023; accepted 21 June 2023; published 28 June 2023)

We study the incubation and transition times that characterize the magnetization switching induced by spinorbit torques in nanomagnets with perpendicular anisotropy. We present a phenomenological model to interpret the dependence of the incubation time on the amplitude of the voltage pulse and assisting magnetic field and estimate the volume of the seed domain that triggers the switching. Our measurements evidence a correlation between the incubation and transition times that is mediated by the temperature variation during the electric pulse. In addition, we discuss the stochastic distributions of the two times in terms of the energy barriers opposing the nucleation and expansion of the seed domain. We propose two models based on the log-normal and gamma functions to account for the different origin of the variability of the incubation and transition times, which are associated with a single nucleation barrier and multiple pinning sites, respectively.

DOI: 10.1103/PhysRevB.107.214447

I. INTRODUCTION

Current-induced magnetization switching by either spintransfer torque (STT) [1-3] or spin-orbit torque (SOT) [4-6] provides the most effective means to achieve electrical control of nanoscale magnetic devices [7,8]. Although the switching can be described theoretically by macrospin models [9,10], the magnetization reversal caused by STT and SOT is, in general, a complex and nonuniform process that involves the nucleation and expansion of magnetic domains [11,12]. This mechanism prevails over the pure macrospin dynamics even in devices as small as a few tens of nm because it is more energetically favorable than the coherent rotation of all the magnetic moments [13–16]. Time-resolved measurements in magnetic tunnel junctions [16-20] and Hall crosses [21] have revealed that the nonuniform switching comprises two phases at the ns and sub-ns timescale: an initial waiting time t_0 during which the magnetization is at rest and the actual transition of duration Δt . The physical mechanisms underlying t_0 and Δt are similar but not identical in the STT and SOT scenarios.

In the STT-driven dynamics, the magnetization is switched by the torque exerted by the spin-polarized current originating from a reference ferromagnetic layer. The initial waiting time t_0 results from the combination of two factors. First, if the electronic spin polarization and the magnetization are collinear, the torque is initially zero and stochastic thermal fluctuations are necessary to trigger the reversal [22]. Second, the formation of the seed domain that initiates the reversal always requires overcoming the energy barrier created by the effective magnetic anisotropy. The duration of the nucleation phase is, therefore, influenced by the temperature increase caused by Joule heating, the magnetic field *B*, and the amplitude of the electric pulses (current density *j* or voltage $V_{\rm P}$) that drive the dynamics. In this case, t_0 is modeled by an Arrhenius-type law with an energy barrier ΔU ,

$$t_0 = \tau e^{\frac{\Delta U}{k_{\rm B}T}},\tag{1}$$

which describes thermally activated processes [2,22-26]. Here, τ^{-1} is the attempt frequency and $k_{\rm B}T$ is the thermal energy. $\Delta U = \Delta U(V_{\rm P}, B)$ generally depends on both $V_{\rm P}$ and B such that higher pulse amplitudes and/or larger magnetic fields result in a strong decrease of the nucleation time [19,22,27,28]. The ensuing domain expansion determines the transition time Δt . Yet, the details of this process depend on the magnetic properties and dimension of the specific sample under investigation as well as the pulse amplitude [22,28,29] The nucleation can take place at the device edge, and the magnetization reversal can be driven by the motion of a single domain wall across the device. In this case, Δt is inversely proportional to the domain-wall speed [16,28,30]. However, theory shows that the switching may also be triggered by magnetostatic instabilities in which different device regions are perturbed differently by the STT [15,29,31]. Under these circumstances, t_0 and Δt may not be associated with two distinct processes.

In the SOT scenario, a spin current is injected into the ferromagnet from an adjacent nonmagnetic layer as a consequence of the spin Hall effect and spin-orbit scattering occurring in the nonmagnet [6,8] [Fig. 1(a)]. Therefore, the spin polarization and the magnetization are orthogonal in perpendicular magnets, and no initial latency is expected [25,32,33]. However, recent experiments have shown that a finite t_0 exists also in the SOT-induced dynamics near the critical switching threshold because the strong energy barrier due to the perpendicular magnetic anisotropy can be more easily overcome with thermal assistance [19–21,34]. The similarity between the STT and SOT dynamics suggests that the

^{*}giacomo.sala@mat.ethz.ch

[†]pietro.gambardella@mat.ethz.ch



FIG. 1. (a) Schematic side view of the device. A perpendicularly magnetized GdFeCo dot (blue) is fabricated on a Pt Hall cross (yellow). Current-induced SOT cause the magnetization switching by domain-wall motion in the presence of a magnetic field \mathbf{B}_x collinear to the current direction j. (b) Schematic top view of the device. The detection of the anomalous Hall voltage $V_{\rm H}$ during the injection of ns-long electric pulses allows us to track the magnetization switching in real time [21]. (c) Schematic side view of the magnetization profile before the nucleation of a domain when the current **j** and magnetic field \mathbf{B}_x are oriented along +x. In Pt/ferromagnet and Pt/ferrimagnet bilayers, the DMI favors inward canting of the magnetic moment when the magnetization is, on average, pointing up. This canting and the global tilt towards +x caused by **B** assist the nucleation of the seed domain by the SOT field \mathbf{B}_{SOT} on the left side. When the magnetization is pointing down, the same combination of current and field leads to the nucleation on the right side (not shown). (d) Schematic of the SOT-induced switching of perpendicular magnets as a function of time (defined by labels I-V). The black-white contrast indicates the sign of the out-of-plane component of the magnetization (m_z) . The switching is driven by the nucleation of a domain at the device edge and the ensuing domain-wall motion. t_0 and Δt are the duration of the two phases, respectively. The sketches in (c) and (d) are adapted from Ref. [12].

nucleation time may be described by an expression similar to Eq. (1) even in the SOT scenario. However, this possibility and the validity of statistical models that capture the stochastic aspects of SOT switching have not been tested thus far. Additionally, the dependence of t_0 on V_P and *B* (applied parallel to the current direction) in the SOT case has never been investigated quantitatively. In the SOT-driven switching of perpendicular magnets, the nucleation of the seed domain usually happens at the device edge because of the combination of SOT, Dzyaloshinkii-Moriya interaction (DMI), and external magnetic field [12,35–38] [see Figs. 1(c) and 1(d)]. Thus, in the SOT scenario, Δt is usually identified with the duration of the domain wall displacement between opposite device edges [12,35–37].

This interpretation remains valid as long as domains can be clearly identified. However, the magnetization reversal in small devices assumes a mixed character that is neither pure macrospin nor domain driven [8]. In this crossover regime, t_0 and Δt are ill-defined and cannot be associated with distinct physical processes. This happens in devices with dimensions comparable to the domain-wall width, typically in the order of 10–50 nm in thin films with perpendicular magnetization [14]. Further, the switching dynamics is expected to change if ps-long current pulses are used to drive the magnetization out-of-equilibrium by reducing the saturation magnetization and magnetic anisotropy at a faster rate than the precessional motion [39]. However, the exact magnetic dynamics at these timescales and the relative importance of torques and Joule heating remain unclear [40,41].

These considerations show that temperature plays a twofold role in both the STT- and SOT-driven dynamics. On the one hand, the temperature increase causes a deterministic variation of the magnetic parameters and, hence, of t_0 and Δt . On the other hand, thermal fluctuations lead to a distribution of the nucleation and transition times. Indeed, nonreproducible dynamics have been observed by time-resolved single-shot measurements of the STT-induced switching [16,18-20,22,34,42-44] and, recently, of the SOTinduced reversal [19-21,34,44]. These measurements show that both t_0 and Δt present in general skewed statistical distributions [16,19-21,27,42,43]. The stochasticity of the STT-driven dynamics has also been analyzed theoretically in a few publications [45-50], but there has been little synergy between the experimental and theoretical approaches. At the experimental level, the choice of a specific distribution to fit the data has been seldom guided by physical considerations. At the theoretical level, exact but rather complex and mathematically nonexplicit distribution functions have been proposed [45-50], which prevent an intuitive understanding of the underlying physical processes and limit the applicability of the derived equations. In addition, most theoretical models rest on the assumption of coherent macrospin dynamics, which is rarely fulfilled.

Here, we provide a simple phenomenological interpretation of the deterministic and stochastic dynamics induced by SOT in perpendicular magnets. We have performed systematic time-resolved Hall measurements of the SOT-induced magnetization switching in ferrimagnetic Pt/GdFeCo dots with perpendicular magnetic anisotropy [21] and have analyzed the influence of the pulse amplitude $V_{\rm P}$, assisting in-plane field B_x , and device size on the mean t_0 and Δt . We propose a phenomenological model to describe the dependence of t_0 on the SOT amplitude, magnetic field, and self-heating. This model validates the qualitative interpretation of the SOT switching as a thermally assisted process, as proposed in previous works [19-21,34,44], and allows us to estimate the volume of the seed domain that initiates the reversal. Our data further evidence a clear correlation between t_0 and Δt that we attribute to the temperature variation during the electric pulse. Finally, we consider the statistical distributions of t_0 and Δt and propose two physically intuitive models based on the lognormal and gamma functions to interpret the stochasticity of the two times. These models suggest a different origin of the stochastical variations of t_0 and Δt , which we associate with a single energy barrier and multiple pinning sites, respectively. Although our analysis focuses on SOT-induced switching, our



FIG. 2. (a) Out-of-plane magnetization of Gd₂₉Fe₆₄Co₇ measured by the anomalous Hall effect during a magnetic field sweep in the *xz* plane at a polar angle $\theta_B = 0^\circ$ and $\theta_B = 87^\circ$ from the normal direction. (b) Exemplary single-shot measurements of the up-down magnetization reversal in a 5-µm-wide device switched by electric pulses with $V_P = 30$ V and 15 ns duration and B = 50 mT applied parallel to the current direction. The straight lines are piecewise linear fits of the quiescent, reversal, and equilibrium phase. The voltage traces are offset for clarity, and the times t_0 and Δt of the first switching event are indicated. Labels I–V refer to Fig. 1(d).

considerations are general and apply also to the magnetization reversal induced by STT. They are also equally valid for ferroand ferrimagnets because our models are independent of the ferrimagnetic order of GdFeCo. The only assumption that we make is that switching occurs by the nucleation and expansion of domains.

II. EXPERIMENT

Figures 1(a) and 1(b) show the structure of our devices and experimental scheme. A 15-nm-thick Gd₂₉Fe₆₄Co₇ pillar is fabricated above a 5-nm-thick Pt Hall cross by optical lithography and ion-beam etching. These devices may be considered equivalent to the lower half of a top-pinned magnetic tunnel junction. Gd₂₉Fe₆₄Co₇ is a ferrimagnet with room-temperature net magnetization $M = M_{\text{FeCo}} - M_{\text{Gd}}$ dominated by the FeCo sublattice and with perpendicular magnetic anisotropy, as indicated by the hysteresis loops in Fig. 2(a). We chose a rare-earth, transition-metal ferrimagnet because of the large anomalous Hall effect of these materials [51], which facilitates time-resolved measurements in Hall crosses [21,52,53]. However, the analysis and considerations presented below are independent of the antiferromagnetic order of ferrimagnetic materials and, hence, apply also to ferromagnets. In addition, in the following, we consider explicitly a pillar with 5 µm diameter, but we have verified that our considerations are valid in devices with smaller dimensions (1, 3, and 4 µm) as well as different composition. In these samples, we have performed time-resolved single-shot Hall measurements of the magnetization switching induced by SOT, as described in detail in Ref. [21]. In short, two electric pulses with the same amplitude but opposite polarity are injected simultaneously into the Pt Hall cross [Fig. 1(b)]. The electric current exerts SOT on the magnetization and, at the same time, generates the anomalous Hall voltage $V_{\rm H}$ proportional to the out-of-plane magnetization. Therefore, the real-time detection of $V_{\rm H}$ allows us to track with 50 ps temporal resolution the orientation of the magnetization excited by SOT. Exemplary time-resolved measurements performed with this approach are presented in Fig. 2(b). Here, the temporal variation of the normalized voltage $V_{\rm H}$ indicates that the reversal comprises three phases: the initial quiescent phase of duration t_0 , the transition during the time Δt , and the final equilibrium phase. As discussed before [19,21], we assume that t_0 and Δt are the times required to nucleate a domain and move the domain wall across the device, respectively [Fig. 1(d)]. Both t_0 and Δt are expected to depend on the pulse amplitude V_P and magnetic field B_x , which is applied collinear to the current direction to ensure the deterministic magnetization reversal [6]. For each combination of these two parameters, we have taken a set of 250 measurements that, after fitting a piecewise linear function to the normalized voltage traces [see Fig. 2(b)], vielded the distributions of the nucleation and transition times. Hereafter, t_0 and Δt will stand for the statistical means of the respective distributions.

III. DEPENDENCE OF t_0 AND Δt ON THE PULSE AMPLITUDE AND MAGNETIC FIELD

Figures 3(a) and 3(d) show the dependence of t_0 and Δt on the pulse amplitude and in-plane magnetic field. Both times decrease upon increasing either parameter, and so do their standard deviations, as also observed in previous works [19–21]. Therefore, the dynamics becomes faster and more reproducible when overdriven. Moreover, for a given pair of current density and magnetic field, both t_0 and Δt decrease with the device diameter d, as shown in Figs. 3(e) and 3(f). The linear scaling of Δt with d corroborates the assumption that the transition time is inversely proportional to the domain-wall speed. Indeed, the dependence of Δt on B_x and $V_{\rm P}$ agrees qualitatively with predictions of the dynamics of domain walls driven by SOT in the presence of a magnetic field [54–57]. In these models, a more intense current exerts stronger torques on the magnetization of the domain wall and speeds up its motion. However, since SOT also pushes the magnetization m away from the current direction, the domainwall velocity tends to saturate [57,58]. The saturation occurs because the dampinglike SOT is proportional to the product $m_x j_c \sim m_x V_P$, which becomes constant in the high current limit. This explains why Δt approaches an asymptotic value at large pulse amplitudes. As shown in Fig. 3(d), the asymptote is influenced by the magnetic field because the latter reorients the saturation magnetization along x, thereby increasing m_x . The same argument explains why Δt decreases as the field is increased at constant pulse amplitude [Fig. 3(c)].

The decrease of Δt with *d* is beneficial to the scalability and speed of spintronic devices. For example, we extrapolate from Fig. 3(e) that the transition time of a 100-nm-wide device could be of the order of 120 ps for a current density of $j_c = 9 \times 10^{11} \text{ A/m}^2$ and a magnetic field B = 60 mT. Thus, the switching could be accomplished with pulses as short as $\approx 150 \text{ ps}$. Decreasing further the diameter would reduce the



FIG. 3. (a), (b) Dependence of the mean nucleation time t_0 on B_x and V_P , respectively. The shaded areas define the standard deviation of the distributions of t_0 . The lines are fits with shared parameters of Eq. (4) to the data. (c), (d) Same as (a), (b) for the transition time Δt . (e) Scaling of Δt with the device diameter *d* for three different combinations of current density and magnetic field. The lines are fit to the data with zero intercept. (f) Scaling of t_0 and t_∞ with *d*. The legend of t_0 is the same as that of Δt in (e). The gray shaded area of t_∞ represents the uncertainty in the fit of Eq. (4) to the field dependence of t_0 .

minimum pulse length necessary to switch the magnetization, but a simple estimate of Δt for $d \ll 100$ nm cannot be drawn from our data because of the onset of coherent dynamics in small devices.

A. Phenomenological model of the dependence of t_0 on the pulse amplitude and magnetic field

As mentioned before, the dependence of t_0 on V_P and B_x has been discussed in the framework of the STT-induced magnetization reversal [2,22–24,26], but these models have not been extended to SOT yet. To fill the gap, we propose here a simple phenomenological model that builds upon the interpretation of the SOT-induced switching as a thermally assisted process [8,19,59]. We argue that the nonzero nucleation time is determined by the energy barrier ΔU that hinders the formation of a reversed domain and its domain wall. This barrier is lowered by the synergetic action of SOT, magnetic field, DMI, and Joule heating [12,19,35,37]. The relationship



FIG. 4. (a) Model of the nucleation of the seed domain at the edge of a magnetic dot starting from an initial state magnetized down. The magnetization **m** at the device edge rotates toward the plane. The gray shading represents this rotation from -z (right) to the *xy* plane (left), which occurs on a lengthscale determined by micromagnetic constraints, i.e., half of the domain-wall width $L = \frac{\delta}{2}$. *w* is the width of the activated area. (b) Variation of the mean transition time with the mean nucleation time. For a given magnetic field, distinct data points correspond to different pulse amplitudes. The solid line is a fit to Eq. (7).

between t_0 and ΔU is captured by an Arrhenius-type law similar to Eq. (1), as typical of thermal processes and similar to the STT-induced dynamics [24,60]. The spread of t_0 is then the result of thermal fluctuations, as discussed later. In this scenario, ΔU equals the energy cost of rotating in plane some of the magnetic moments at the edge of the dot, where the reversal starts [12,35] [see Figs. 1(d) and 4(a)], and may be expressed as follows:

$$\Delta U = \Delta U_B + \Delta U_{\text{ex}} + \Delta U_{\text{k}} + \Delta U_{\text{DMI}} = \Delta U_B + \Delta U_0.$$
(2)

Here, we consider the contributions of the Zeeman energy ΔU_B , exchange energy ΔU_{ex} , effective anisotropy energy $\Delta U_{\rm k}$, and DMI $\Delta U_{\rm DMI}$, and assume that $\Delta U_0 = \Delta U_{\rm ex} +$ $\Delta U_{\rm k} + \Delta U_{\rm DMI}$ is independent of the applied magnetic field. This assumption does not affect the validity of our model, which could be refined to include, for example, the field dependence of the effective anisotropy. The independence of the exchange, anisotropy, and DMI energy of the magnetic field is consistent with the so-called droplet model [38,61]. The present analysis can be considered as a reformulation of this model with no explicit reference to the analytical form of ΔU_0 . In general, we expect a decrease of the magnetization and anisotropy caused by Joule heating [19] and, hence, a dependence of ΔU on the applied voltage. Further, we postulate that the SOT itself contributes to the reduction of the energy barrier. In principle, a well-defined energy associated with the torques does not exist because the corresponding effective fields cannot be derived from an energy functional [6,24]. However, it is still possible to conceive an effective torque contribution to the energy barrier, as is often assumed in the STT theory [22–25,31,60]. The direct (via the SOT) and indirect (via Joule heating) effects of the pulse amplitude on the energy barrier are unknown and may not have the same functional dependence on $V_{\rm P}$. Therefore, we assume for simplicity that, to the lowest order, ΔU can be corrected by a

$$t_0(V_{\rm P}, B_x) = \tau(V_{\rm P})e^{\frac{\Delta U(B_x) - \gamma V_{\rm P}}{k_{\rm B}T + \eta V_{\rm P}^2}},\tag{3}$$

where ηV_P^2 accounts for the temperature increase caused by the current. $\tau(V_P)$ is a characteristic time that could depend on both V_P and B_x [2,26]. Since the dependence of t_0 on B_x resembles a simple exponential [see Fig. 3(a)], we assume that the effect of the field on τ , if any, is negligible. This assumption is corroborated *a posteriori* by the good quality of the fits in Fig. 3(a), as discussed later. On the other hand, the data in Fig. 3(b) do not exclude that τ might depend on the voltage, so we keep the notation $\tau(V_P)$.

A final point to consider is the finite asymptotic value of t_0 when $B_x, V_P \to \infty$. We do not have a conclusive explanation for the existence of a finite intrinsic nucleation time t_{∞} , which is of the order of 1.5 ns in Figs. 3(a) and 3(b). However, we have observed that t_{∞} decreases with the dimension of the device and becomes negligible within the temporal resolution of our measurements and the precision of the fits in 3-µm-wide dots. A likely explanation is the following. The incubation time t_0 is obtained from the fits under the assumption that the nucleation leads to an appreciable variation of the time-resolved anomalous Hall voltage. If we assume that the volume of the seed domain is independent of the device size (see below), the relative variation of this signal becomes smaller and more difficult to detect in larger devices. In such a case, t_{∞} represents an artifact of the measurement without any physical meaning. This explanation is supported by the decrease of t_{∞} with the device diameter d in Fig. 3(f). We also note that the rather large value of t_{∞} cannot be ascribed to any known magnetic dynamics, which should have much shorter timescales in the limit $B_x, V_P \to \infty$. In any case, t_∞ does not impact the validity of the model of t_0 , its stochastic properties, and the estimate of the seed volume.

Taking into account this temporal offset, we express the dependence of t_0 on B_x and V_P as

$$t_0(V_{\rm P}, B_x) = t_\infty + \tau'(V_{\rm P})e^{-B_x/\beta},$$
 (4)

where

$$\beta = \frac{\left(k_{\rm B}T + \eta V_{\rm P}^2\right)B_x}{\Delta U_B(B_x)} = \frac{\left(k_{\rm B}T + \eta V_{\rm P}^2\right)}{cM_{\rm s}},\qquad(5)$$

$$\tau'(V_{\rm P}) = \tau(V_{\rm P})e^{\frac{\Delta U_0 - \gamma V_{\rm P}}{k_B T + \eta V_{\rm P}^2}}.$$
(6)

The parameter β represents an effective magnetic field, and *c* depends on the volume of the seed domain and on the magnetization orientation, as discussed below. Given the dependence of β on the temperature and saturation magnetization M_s , we interpret it as a fictitious field assisting the reversal, analogous to the thermal field used in micromagnetics to account for stochastic thermal effects [62,63]. As shown in Fig. 3(a), Eq. (4) captures well the dependence of the nucleation time on the magnetic field. The fits of t_0 to Eq. (4) yield $\beta \approx 23 \pm 2$ mT, with a slight increase of β with the voltage, in accordance with Eq. (5). Equation (4) also reproduces the dependence of t_0 on the voltage, which is not simply exponential because of Joule heating [Fig. 3(b)]. The good quality of the fits confirms that the nucleation is a dynamical process

associated with a single energy barrier and validates our model, which also allows for estimating the volume V of the reversed domain, as shown below.

B. Estimate of the activation volume

We assume that the smallest activated volume has a length L along x, starting from the device edge, that equals at least half of a domain wall width $L = \frac{\delta}{2}$ [see Fig. 4(a)]. Here, we estimate $\delta \approx 35$ nm based on the measured magnetic anisotropy and exchange stiffness of about 2 pJ/m reported in the literature for GdFeCo [64–66]. $\mathscr{A} = wt_{FM}$ is the surface of the domain wall in the yz plane, and $t_{\rm FM} = 15$ nm is the thickness of GdFeCo. Before the nucleation, the magnetic moments are oriented at an average angle θ to the z axis determined by the external field. This angle can be determined from the hysteresis loop in Fig. 2(a), for example $\theta = 32^{\circ}$ at 100 mT. With the field angle $\theta_B = 90^\circ$, we can write the initial Zeeman energy as $U_B = \frac{\delta}{2} \mathscr{A} M_s B \sin \theta$, where $M_s = 113$ kA/m. To calculate the Zeeman energy U'_B after the nucleation, we assume that the domain wall is of Néel type because of the finite DMI of Pt/ferrimagnet bilayers [67-69] and applied in-plane magnetic field. In this case, $\theta'(x) = 2 \arctan(e^{\frac{x}{\delta}})$ [70] and $U'_B \approx \int_0^{\frac{\delta}{2}} \mathscr{A} M_{\rm s} B \sin \theta' \, dx = 0.48 \delta \mathscr{A} M_{\rm s} B$. Thus, c = $\delta \mathscr{A}(0.48 - \frac{\sin \theta}{2})$ and $\beta = \frac{k_{\rm B}T + \eta V_{\rm P}^2}{\delta \mathscr{A} M_{\rm s}(0.48 - \frac{\sin \theta}{2})}$. If we take $k_{\rm B}T +$ $\eta V_{\rm P}^2 \approx k_{\rm B} \times 350 \,{\rm K}$, we find $\mathcal{V} = \frac{\delta}{2} \mathscr{A} = 4300 \,{\rm nm}^3$, $\mathscr{A} =$ 240 nm^2 , and w = 16 nm. The estimated activation volume is in good agreement with other estimates obtained from measurements of the field-induced magnetization reversal and domain-wall depinning, which yield $\mathcal{V} \approx 8 \times 10^3 \text{ nm}^3$ [13,71,72]. This calculation indicates that the activated region is much smaller than the dot size and corresponds to the smallest reversed volume compatible with micromagnetic constraints. We also note that this estimation is independent of the dot dimension as long as the device is much larger than the domain-wall width. In future studies, it may be interesting to verify how the device shape influences the size of the seed volume. Estimating the dimension of the seed domain can be useful to identify the critical dimension at which the transition from the domain-wall driven to the macrospin dynamics occurs, which is relevant to the downscaling of devices.

IV. CORRELATION BETWEEN t_0 AND Δt

Because the nucleation always precedes the expansion of the seed domain, it is interesting to investigate the relationship between t_0 and Δt . Figure 4(b) shows that t_0 and Δt correlate over several combinations of the pulse amplitude and magnetic field. In general, we find that the data points follow the same universal curve, and the longer t_0 , the shorter Δt is. The relation is not simply linear. However, a simple way to explain the overall trend in Fig. 4(b) is based on the assumption that temperature mediates the correlation between the two times. The domain-wall speed v in a ferrimagnet depends on several parameters but, if we retain only those that are, in principle, temperature dependent, we may write $v \sim \frac{\partial \theta_{\text{SHE}}}{\alpha(g_2M_1+g_1M_2)}$ (g_i and M_i are the Landé g-factor and the saturation magnetization of the *i*th sublattice) [73]. The spin Hall angle θ_{SHE} is not expected to vary significantly with



FIG. 5. (a), (b) Distributions of the nucleation and transition time, respectively, at different magnetic fields and for a pulse amplitude $V_P = 30$ V. The data sets include 250 measurements. The bin size is 100 ps, larger than the nominal temporal resolution of 50 ps, for ease of visualization. (c), (d) Cumulative distributions obtained from the data in (a), (b) and fits (solid lines) to the log-normal and Gamma cumulative distribution function, respectively.

temperature since the spin Hall effect in Pt is of intrinsic origin, nor is the effective damping α of GdFeCo [69]. Since the exchange stiffness and anisotropy can be expressed as powers of $\sim (\frac{M(T)}{M_s})^p$ of the net magnetization [19,74,75], which in turn depends on temperature according to a power law of the form $M(T) \sim (1 - \frac{T}{T_c})^q$, we can write that $\Delta t \sim 1/v \sim (g_2 M_1 + g_1 M_2) \sqrt{\frac{k_{\rm eff}}{A_{\rm ex}}} \sim (1 - \frac{T}{T_c})^k$, with T_c the Curie temperature and k an appropriate exponential. Further, finite-element COMSOL simulations show that the increase in time of temperature caused by Joule heating is governed by a law of the type $T(t) = T_0 + \Delta T (1 - e^{-\frac{t}{\tau_T}})$, where T_0 is the ambient temperature, ΔT the maximum temperature variation, and τ_T the corresponding time constant. Upon setting $t = t_0$, we obtain

$$\Delta t \sim \left(E + F e^{-\frac{t_0}{\tau_T}} \right)^k,\tag{7}$$

where $E^k \approx 8$ ns and $(E + F)^k \approx 2.8$ ns are the transition time in the long and short nucleation time regimes, respectively. As shown in Fig. 4(b), Eq. (7) can fit well the dependence of Δt on t_0 with $k \approx -0.6$ and $\tau_T \approx 2$ ns despite our simplifications. This result supports our hypothesis of a correlation between the two times mediated by temperature.

V. STATISTICAL DISTRIBUTIONS OF t_0 AND Δt

Time-resolved Hall measurements also provide insight into the stochastic nature of the dynamics. Figures 5(a) and 5(b)show exemplary distributions of the nucleation and transition times at different in-plane magnetic fields. As the field increases, both the mean and standard deviation of the distributions decrease [19,20,28], in accordance with the trends in Figs. 3(a) and 3(c). The distributions show a similar trend when the control parameter is the pulse amplitude because in the limit of large V_P the dynamics is essentially dictated by SOT [46].

As a first attempt, we may choose the Gaussian function to describe the variability of t_0 and Δt because thermal fluctuations are usually assumed to be Gaussian distributed [62,76]. We find, indeed, that the Gaussian function fits reasonably well the distributions of both t_0 and Δt (not shown). However, we argue that this function does not provide the correct statistics of the two characteristic times. In fact, both t_0 and Δt are lower bounded, i.e., they cannot be smaller than 0. Therefore, we expect that in the limit of large $V_{\rm P}$ and B_x the skewness of the distributions increases because of the accumulation of data points near 0. Although this tendency is not clearly observable in Figs. 5(a) and 5(b), skewed distributions were found in former measurements of similar ferro- and ferrimagnetic samples [16,18–21,43]. This evidence indicates the need for alternative statistical models, which, in the case of Δt , cannot simply be the exponential function that is sometimes used to model the depinning time of domain walls [22,42,77]. Here we adopt a phenomenological approach and propose distinct distributions for t_0 and Δt with a direct physical interpretation.

A. Interpretation of the stochasticity of t_0

According to Eq. (1), the nucleation time is a function of the energy barrier ΔU , hence, its variability stems directly from fluctuations of ΔU . If we assume that such fluctuations are of thermal origin and hence Gaussian distributed [62,76], then the statistics of t_0 is log normal [78] because the exponential function $Y = e^X$ of a normally distributed random variable X has log-normal distribution. As shown in Fig. 5(c), the cumulative distribution function. Although the Gaussian and gamma functions fit equally well to the cumulative distributions in Fig. 5(c), we consider the log-normal function a mathematically and physically sound statistics for the nucleation time. It is associated with the overcome of an energy barrier, independently of whether SOT or another force drives the nucleation.

Indeed, in a mean-field model, the energy barrier ΔU is a macroscopic quantity obtained by summing the microscopic energies U_i of all the magnetic moments involved in the nucleation of a seed domain. The macroscopic fluctuations of ΔU are approximately the sum of the microscopic random variations of U_i , that is, ΔU is a random variable with Gaussian distribution. As a consequence, $t_0 \sim e^{\frac{\Delta U}{k_B T}} \approx \prod_i e^{\frac{U_i}{k_B T}}$ is a log-normal variable because the product of many independent random variables approaches the log-normal distribution, in the same way as the sum of many independent variables is normally distributed. This reasoning indicates that, at the macroscopic level, independent thermal fluctuations are multiplicative, not additive. Moreover, it implies that the standard deviation of t_0 grows exponentially with the number of involved magnetic moments, that is, with the dimension of the seed domain. This implication may be examined in future works. Note that a log-normal distribution only admits positive values, consistently with t_0 , $\Delta t > 0$.

B. Interpretation of the stochasticity of Δt

The motion of a domain wall is influenced by both thermal fluctuations and local variations of the pinning potential. Micromagnetic simulations that only include the thermal field predict a Gaussian distribution of depinning times [76]. However, previous experimental work has found evidence of more complex statistics [46,79], and exponential [25,77], log-normal [78], and gamma [80] functions have been used to describe the distributions of depinning times from notches or constrictions. Simple physical considerations, however, support the choice of a specific distribution. The transition time is associated with the high-speed and nearly continuous motion of the domain wall in a small and confined device [12,37]. During its propagation, the domain wall can encounter multiple independent pinning sites in the form of local variations of the magnetic properties, surface and edge roughness, and device geometry. The transition time is therefore the sum of the times Δt_i taken to move from one pinning point to the next and the depinning times at each site t_j : $\Delta t = \sum_i \Delta t_i + \sum_j t_j$. We assume for simplicity that the time intervals Δt_i are nearly deterministic and determined uniquely by the domain-wall speed, which is in turn set by the external magnetic field and SOT. In contrast, we consider the depinning times t_i as the main source of stochasticity. We show now that the nature of the pinning determines the overall statistical distribution of Δt .

If the depinning process is statistically described by an exponential distribution, as often assumed [22,42,77,81], then the sum $\sum_{i} t_i$ and, hence, Δt is mathematically a random variable with gamma distribution [82,83]. If, instead, we assume that each depinning time behaves similarly to t_0 and is thus a log-normal variable, then Δt is a random variable with no explicit statistical distribution because the sum of log-normal variables resembles but is not a log-normal distribution. In practice, the overall pinning landscape may encompass different pinning potentials with distinct distribution functions, such that the overall statistic of Δt depends on the details of the sample [79]. In the present case, we find that the cumulative gamma function fits well to the cumulative distributions of Δt , as shown in Fig. 5(d). A more extensive investigation as a function of the sample material and geometry is needed to ascertain the actual nature of the stochasticity of Δt . We note, however, that the gamma distribution offers an interesting connection with other physical phenomena. Gamma-distributed events are particular cases of a Lévy process, which is the simplest process consisting of a continuous motion with jumps of random size occurring at random times [84]. For instance, the Poisson process and the Brownian motion, which is the continuous-time version of a random walk, are Lévy processes. The field- or currentdriven dynamics of domain walls share these features because the domain expansion may be interpreted as the continuous motion of a domain wall interspersed by random occurrences (pinning) that alter its speed. The accumulation of successive random events represents a fundamental difference between the variability of Δt and t_0 .

Our considerations on the stochasticity of t_0 and Δt are based on the physical processes described by the nucleation and transition times and do not refer to specific experimental conditions. They are general and remain valid independently of the amplitude and duration of the electric pulses or the strength of the magnetic field. Moreover, our model is independent of the magnetic properties of the sample under investigation and is expected to lose validity only when the magnetic dynamics approach the macrospin regime, i.e., in devices smaller than a few tens of nm.

VI. CONCLUSIONS

We have analyzed the dependence of the nucleation time t_0 and transition time Δt on the pulse amplitude V_P and assisting in-plane magnetic field B_x during the SOT-induced switching of perpendicularly magnetized GdFeCo dots. We have found that the decrease of Δt with V_P and B_x can be interpreted according to existing models of the domain wall motion driven by SOT. On the other hand, we have proposed a framework to understand the variation of t_0 with current and field and provided an estimate of the dimensions of the nucleated domain. In our model, t_0 depends on the activation energy required to nucleate a seed domain against a single energy barrier determined by the magnetic anisotropy, the Zeeman energy, and the DMI. We have also revealed the existence of a correlation between t_0 and Δt established by the temperature variation during the switching.

Finally, we have discussed the physical origin of the stochasticity of the two times, which decreases with strong pulses or magnetic fields. The variability of t_0 is associated with thermal fluctuations of a single energy barrier and is captured by a log-normal function. Instead, the distributions of Δt can be interpreted in terms of a cumulative process of random events associated with distinct pinning sites. The exact analytical function describing the statistical distribution of Δt depends on the details of the pinning landscape but can be approximated by a gamma distribution. We expect these statistical considerations to be valid also for the STT-induced magnetization switching because the reversal mechanism (nucleation and domain expansion) is to some extent similar to that triggered by SOT, and we do not make explicit reference to the driving force of the dynamics. Overall, our study provides insight into the deterministic and stochastic aspects of the magnetization switching induced by electric currents.

ACKNOWLEDGEMENT

We acknowledge the support of the Swiss National Science Foundation (Grant No. 200020-200465).

- [1] E. B. Myers, D. C. Ralph, J. A. Katine, R. N. Louie, and R. A. Buhrman, Science 285, 867 (1999).
- [2] J.-E. Wegrowe, O. Fruchart, J.-P. Nozières, D. Givord, F. Rousseaux, D. Decanini, and J. P. Ansermet, J. Appl. Phys. 86, 1028 (1999).
- [3] M. D. Stiles and A. Zangwill, Phys. Rev. B 66, 014407 (2002).
- [4] I. M. Miron, K. Garello, G. Gaudin, P.-J. Zermatten, M. V. Costache, S. Auffret, S. Bandiera, B. Rodmacq, A. Schuhl, and P. Gambardella, Nature (London) 476, 189 (2011).

- [5] L. Liu, C.-F. Pai, Y. Li, H. W. Tseng, D. C. Ralph, and R. A. Buhrman, Science 336, 555 (2012).
- [6] A. Manchon, J. Železný, I. M. Miron, T. Jungwirth, J. Sinova, A. Thiaville, K. Garello, and P. Gambardella, Rev. Mod. Phys. 91, 035004 (2019).
- [7] A. V. Khvalkovskiy, D. Apalkov, S. Watts, R. Chepulskii, R. S. Beach, A. Ong, X. Tang, A. Driskill-Smith, W. H. Butler, P. B. Visscher, D. Lottis, E. Chen, V. Nikitin, and M. Krounbi, J. Phys. D 46, 139601 (2013).
- [8] V. Krizakova, M. Perumkunnil, S. Couet, P. Gambardella, and K. Garello, J. Magn. Magn. Mater. 562, 169692 (2022).
- [9] J. Z. Sun, Phys. Rev. B 62, 570 (2000).
- [10] K.-S. Lee, S.-W. Lee, B.-C. Min, and K.-J. Lee, Appl. Phys. Lett. 102, 112410 (2013).
- [11] D. P. Bernstein, B. Bräuer, R. Kukreja, J. Stöhr, T. Hauet, J. Cucchiara, S. Mangin, J. A. Katine, T. Tyliszczak, K. W. Chou, and Y. Acremann, Phys. Rev. B 83, 180410(R) (2011).
- [12] M. Baumgartner, K. Garello, J. Mendil, C. O. Avci, E. Grimaldi, C. Murer, J. Feng, M. Gabureac, C. Stamm, Y. Acremann, S. Finizio, S. Wintz, J. Raabe, and P. Gambardella, Nat. Nanotechnol. **12**, 980 (2017).
- [13] J. Z. Sun, R. P. Robertazzi, J. Nowak, P. L. Trouilloud, G. Hu, D. W. Abraham, M. C. Gaidis, S. L. Brown, E. J. O'Sullivan, W. J. Gallagher, and D. C. Worledge, Phys. Rev. B 84, 064413 (2011).
- [14] G. D. Chaves-O'Flynn, G. Wolf, J. Z. Sun, and A. D. Kent, Phys. Rev. Appl. 4, 024010 (2015).
- [15] J. Beik Mohammadi and A. D. Kent, Appl. Phys. Lett. 118, 132407 (2021).
- [16] P. Bouquin, J.-V. Kim, O. Bultynck, S. Rao, S. Couet, G. S. Kar, and T. Devolder, Phys. Rev. Appl. 15, 024037 (2021).
- [17] T. Devolder, J. Hayakawa, K. Ito, H. Takahashi, S. Ikeda, P. Crozat, N. Zerounian, J.-V. Kim, C. Chappert, and H. Ohno, Phys. Rev. Lett. **100**, 057206 (2008).
- [18] H. Tomita, K. Konishi, T. Nozaki, H. Kubota, A. Fukushima, K. Yakushiji, S. Yuasa, Y. Nakatani, T. Shinjo, M. Shiraishi, and Y. Suzuki, Appl. Phys. Express 1, 061303 (2008).
- [19] E. Grimaldi, V. Krizakova, G. Sala, F. Yasin, S. Couet, G. Sankar Kar, K. Garello, and P. Gambardella, Nat. Nanotechnol. 15, 111 (2020).
- [20] V. Krizakova, K. Garello, E. Grimaldi, G. S. Kar, and P. Gambardella, Appl. Phys. Lett. 116, 232406 (2020).
- [21] G. Sala, V. Krizakova, E. Grimaldi, C.-H. Lambert, T. Devolder, and P. Gambardella, Nat. Commun. 12, 656 (2021).
- [22] O. Bultynck, M. Manfrini, A. Vaysset, J. Swerts, C. J. Wilson, B. Sorée, M. Heyns, D. Mocuta, I. P. Radu, and T. Devolder, Phys. Rev. Appl. **10**, 054028 (2018).
- [23] R. H. Koch, J. A. Katine, and J. Z. Sun, Phys. Rev. Lett. 92, 088302 (2004).
- [24] Z. Li and S. Zhang, Phys. Rev. B 69, 134416 (2004).
- [25] D. Bedau, H. Liu, J. Z. Sun, J. A. Katine, E. E. Fullerton, S. Mangin, and A. D. Kent, Appl. Phys. Lett. 97, 262502 (2010).
- [26] L. Desplat and J.-V. Kim, Phys. Rev. Lett. 125, 107201 (2020).
- [27] F. Iga, Y. Yoshida, S. Ikeda, T. Hanyu, H. Ohno, and T. Endoh, Jpn. J. Appl. Phys. 51, 02BM02 (2012).
- [28] C. Hahn, G. Wolf, B. Kardasz, S. Watts, M. Pinarbasi, and A. D. Kent, Phys. Rev. B 94, 214432 (2016).
- [29] P. B. Visscher, K. Munira, and R. J. Rosati, arXiv:1604.03992.

- [30] T. Devolder, J.-V. Kim, J. Swerts, S. Couet, S. Rao, W. Kim, S. Mertens, G. Kar, and V. Nikitin, IEEE Trans. Magn. 54, 3400109 (2018).
- [31] K. Munira and P. B. Visscher, J. Appl. Phys. 117, 17B710 (2015).
- [32] H. Liu, D. Bedau, J. Z. Sun, S. Mangin, E. E. Fullerton, J. A. Katine, and A. D. Kent, J. Magn. Magn. Mater. 358–359, 233 (2014).
- [33] K. Garello, C. O. Avci, I. M. Miron, M. Baumgartner, A. Ghosh, S. Auffret, O. Boulle, G. Gaudin, and P. Gambardella, Appl. Phys. Lett. 105, 212402 (2014).
- [34] W. Cai, K. Shi, Y. Zhuo, D. Zhu, Y. Huang, J. Yin, K. Cao, Z. Wang, Z. Guo, Z. Wang, G. Wang, and W. Zhao, IEEE Electron Device Lett. 42, 704 (2021).
- [35] N. Mikuszeit, O. Boulle, I. M. Miron, K. Garello, P. Gambardella, G. Gaudin, and L. D. Buda-Prejbeanu, Phys. Rev. B 92, 144424 (2015).
- [36] E. Martinez, L. Torres, N. Perez, M. A. Hernandez, V. Raposo, and S. Moretti, Sci. Rep. 5, 10156 (2015).
- [37] G. Sala, C.-h. Lambert, S. Finizio, V. Raposo, V. Krizakova, G. Krishnaswamy, M. Weigand, J. Raabe, M. D. Rossell, E. Martinez, and P. Gambardella, Nat. Mater. 21, 640 (2022).
- [38] S. Pizzini, J. Vogel, S. Rohart, L. D. Buda-Prejbeanu, E. Jué, O. Boulle, I. M. Miron, C. K. Safeer, S. Auffret, G. Gaudin, and A. Thiaville, Phys. Rev. Lett. 113, 047203 (2014).
- [39] K. Jhuria, J. Hohlfeld, A. Pattabi, E. Martin, A. Y. Arriola Córdova, X. Shi, R. Lo Conte, S. Petit-Watelot, J. C. Rojas-Sanchez, G. Malinowski, S. Mangin, A. Lemaître, M. Hehn, J. Bokor, R. B. Wilson, and J. Gorchon, Nat. Electron. 3, 680 (2020).
- [40] Y. Yang, R. B. Wilson, J. Gorchon, C. H. Lambert, S. Salahuddin, and J. Bokor, Sci. Adv. 3, e1603117 (2017).
- [41] R. B. Wilson, J. Gorchon, Y. Yang, C.-H. Lambert, S. Salahuddin, and J. Bokor, Phys. Rev. B 95, 180409(R) (2017).
- [42] Y. T. Cui, G. Finocchio, C. Wang, J. A. Katine, R. A. Buhrman, and D. C. Ralph, Phys. Rev. Lett. **104**, 097201 (2010).
- [43] H. Zhao, Y. Zhang, P. K. Amiri, J. A. Katine, J. Langer, H. Jiang, I. N. Krivorotov, K. L. Wang, and J.-P. Wang, IEEE Trans. Magn. 48, 3818 (2012).
- [44] V. Krizakova, E. Grimaldi, K. Garello, G. Sala, S. Couet, G. S. Kar, and P. Gambardella, Phys. Rev. Appl. 15, 054055 (2021).
- [45] Z. Diao, Z. Li, S. Wang, Y. Ding, A. Panchula, E. Chen, L. C. Wang, and Y. Huai, J. Phys.: Condens. Matter 19, 165209 (2007).
- [46] A. F. Vincent, N. Locatelli, J. O. Klein, W. S. Zhao, S. Galdin-Retailleau, and D. Querlioz, IEEE Trans. Electron Devices 62, 164 (2015).
- [47] J.-H. Moon, T. Y. Lee, and C.-Y. You, Sci. Rep. 8, 13288 (2018).
- [48] G. Siracusano, R. Tomasello, M. D'Aquino, V. Puliafito, A. Giordano, B. Azzerboni, P. Braganca, G. Finocchio, and M. Carpentieri, IEEE Trans. Magn. 54, 1400210 (2018).
- [49] M. d'Aquino, S. Perna, and C. Serpico, Phys. B: Condens. Matter 577, 411744 (2020).
- [50] A. Shukla, A. Parthasarathy, and S. Rakheja, Phys. Rev. Appl. 13, 054020 (2020).
- [51] Y. Mimura, N. Imamura, T. Kobayashi, A. Okada, and Y. Kushiro, J. Appl. Phys. 49, 1208 (1978).
- [52] G. K. Krishnaswamy, G. Sala, B. Jacot, C.-H. Lambert, R. Schlitz, M. D. Rossell, P. Nöel, and P. Gambardella, Phys. Rev. Appl. 18, 024064 (2022).

- [53] G. Sala and P. Gambardella, Adv. Mater. Interfaces 9, 2201622 (2022).
- [54] P. P. J. Haazen, E. Murè, J. H. Franken, R. Lavrijsen, H. J. M. Swagten, and B. Koopmans, Nat. Mater. 12, 299 (2013).
- [55] S. Emori, U. Bauer, S.-M. Ahn, E. Martinez, and G. S. D. Beach, Nat. Mater. 12, 611 (2013).
- [56] S. Emori, E. Martinez, K.-J. Lee, H.-W. Lee, U. Bauer, S.-M. Ahn, P. Agrawal, D. C. Bono, and G. S. D. Beach, Phys. Rev. B 90, 184427 (2014).
- [57] E. Martinez, S. Emori, N. Perez, L. Torres, and G. S. D. Beach, J. Appl. Phys. **115**, 213909 (2014).
- [58] S.-H. Yang, K.-S. Ryu, and S. Parkin, Nat. Nanotechnol. 10, 221 (2015).
- [59] K.-S. Lee, S.-W. Lee, B.-C. Min, and K.-J. Lee, Appl. Phys. Lett. 104, 072413 (2014).
- [60] R. Lo Conte, A. Hrabec, A. P. Mihai, T. Schulz, S. J. Noh, C. H. Marrows, T. A. Moore, and M. Kläui, Appl. Phys. Lett. 105 (2014).
- [61] S. Kim, P.-H. Jang, D.-H. Kim, M. Ishibashi, T. Taniguchi, T. Moriyama, K.-J. Kim, K.-J. Lee, and T. Ono, Phys. Rev. B 95, 220402(R) (2017).
- [62] W. F. Brown, J. Appl. Phys. 34, 1319 (1963).
- [63] J. L. García-Palacios and F. J. Lázaro, Phys. Rev. B 58, 14937 (1998).
- [64] W. Xian-Ying, Z. Yue-Pin, L. Zuo-Yi, S. De-Fang, and G. Fu-Xi, Chin. Phys. Lett. 20, 1359 (2003).
- [65] D. Raasch, J. Reck, C. Mathieu, and B. Hillebrands, J. Appl. Phys. 76, 1145 (1994).
- [66] F. Radu and J. Sánchez-Barriga, in *Novel Magnetic Nanostructures* (Elsevier, 2018), Chap. 9, pp. 267–331.
- [67] J. Finley and L. Liu, Phys. Rev. Appl. 6, 054001 (2016).
- [68] K. Shahbazi, J.-V. Kim, H. T. Nembach, J. M. Shaw, A. Bischof, M. D. Rossell, V. Jeudy, T. A. Moore, and C. H. Marrows, Phys. Rev. B 99, 094409 (2019).
- [69] D.-H. Kim, T. Okuno, S. K. Kim, S.-H. Oh, T. Nishimura, Y. Hirata, Y. Futakawa, H. Yoshikawa, A. Tsukamoto, Y. Tserkovnyak, Y. Shiota, T. Moriyama, K.-J. Kim, K.-J. Lee, and T. Ono, Phys. Rev. Lett. **122**, 127203 (2019).

- [70] A. Mougin, M. Cormier, J. P. Adam, P. J. Metaxas, and J. Ferré, Europhys. Lett. 78, 57007 (2007).
- [71] W. Wernsdorfer, K. Hasselbach, A. Benoit, B. Barbara, B. Doudin, J. Meier, J.-P. Ansermet, and D. Mailly, Phys. Rev. B 55, 11552 (1997).
- [72] C. Wuth, P. Lendecke, and G. Meier, J. Phys.: Condens. Matter 24, 024207 (2012).
- [73] E. Martínez, V. Raposo, and Ó. Alejos, J. Magn. Magn. Mater. 491, 165545 (2019).
- [74] R. Moreno, R. F. L. Evans, S. Khmelevskyi, M. C. Muñoz, R. W. Chantrell, and O. Chubykalo-Fesenko, Phys. Rev. B 94, 104433 (2016).
- [75] Y. Hirata, D.-H. Kim, T. Okuno, T. Nishimura, D.-Y. Kim, Y. Futakawa, H. Yoshikawa, A. Tsukamoto, K.-J. Kim, S.-B. Choe, and T. Ono, Phys. Rev. B 97, 220403(R) (2018).
- [76] E. Martinez, L. Lopez-Diaz, O. Alejos, L. Torres, and C. Tristan, Phys. Rev. Lett. 98, 267202 (2007).
- [77] C. Burrowes, A. P. Mihai, D. Ravelosona, J.-V. Kim, C. Chappert, L. Vila, A. Marty, Y. Samson, F. Garcia-Sanchez, L. D. Buda-Prejbeanu, I. Tudosa, E. E. Fullerton, and J.-P. Attané, Nat. Phys. 6, 17 (2010).
- [78] T. Taniguchi, K.-J. Kim, Y. Yoshimura, T. Moriyama, H. Tanigawa, T. Suzuki, E. Kariyada, and T. Ono, Appl. Phys. Express 7, 053005 (2014).
- [79] M.-Y. Im, L. Bocklage, P. Fischer, and G. Meier, Phys. Rev. Lett. 102, 147204 (2009).
- [80] P. J. Metaxas, J. Sampaio, A. Chanthbouala, R. Matsumoto, A. Anane, A. Fert, K. A. Zvezdin, K. Yakushiji, H. Kubota, A. Fukushima, S. Yuasa, K. Nishimura, Y. Nagamine, H. Maehara, K. Tsunekawa, V. Cros, and J. Grollier, Sci. Rep. 3, 1829 (2013).
- [81] J. P. Attané, D. Ravelosona, A. Marty, Y. Samson, and C. Chappert, Phys. Rev. Lett. 96, 147204 (2006).
- [82] S. S. Gupta, Technometrics 2, 243 (1960).
- [83] W. J. McGill and J. Gibbon, J. Math. Psychol. 2, 1 (1965).
- [84] D. Applebaum, Notices of the AMS 51, 1336 (2004).